

TEST REPORT NUMBER: TSNT01791373





TEST REPORT NUMBER: TSNT01791373

Date:

Mar 25, 2025

Applicant: Beijing Embfan Tech. Limited

Room 609, Unit 2, Building 5, Zhujiang Moore International

Building, No.1 Beiging Road, Changping District, Beijing PRC.

Attn Wei Sheng

Sample Description As Declared:

One (1) No. Of Sample

Fibre Content 100% Polyester

Material Knitted Mesh Fabric RPET, 150gsm

Finishing **End Uses** Colour Navy Style No. Order No./PO No. Buyer's Name **BUCK**

Agent's Name Manufacturer's Name

Applicant's Provided Care Instruction/Label:-

Date Received/Date Test Started: Mar 19, 2025

Persnicle

Tests Conducted:

As Requested By The Applicant, For Details Refer To Attached Page(S)

Authorized By:

For Intertek Testing Services

(Tianjin) Ltd.

Patrick Gong General Manager



NUMBER: TSNT01791373

Tests Conducted:

1 Recycled Polyester Test:

By Chemical Analysis To Determine Isophthalic Acid (IPA) In Recycled Polyester Fiber Made From PET Bottles With Gas Chromatography – Tandem Mass Spectrometry (GC-MS).

<u>Tested Sample</u>	Isophthalic Acid (IPA) content in %	Recycled Polyester Content made from PET bottles - indicative result #	<u>Conclusion</u>
Submitted Sample	1.3	> 75%	Likely Contains Recycled Polyester Fiber Made From PET Bottles.

Remark: Detection Limit = 0.1% IPA Content Of Polyester Fiber Content
(Corresponding To Approximate 10% Recycled Polyester Fiber Made From PET Bottles)

= Calculation Of Recycled Polyester Content Is Based On An Average IPA Content Of 1.6 % Found In PET Bottles. In Addition, It Is Assumed That The IPA Content Determined In The Investigated Sample Entirely Originates From Recycled PET Bottles. Due To The Relatively High Variation Of The IPA Content In PET Bottles, The Reported Recycled Polyester Content Only Serves As A Benchmark.

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.